

AMENDMENTS TO THE SPECIFICATION

Please replace the paragraph beginning at page 5, line 2, with the following rewritten paragraph:

Component (D): An elastomeric styrene polymer which comprises from 99 to 85 parts by mass of a continuous phase comprising from 35 to 75 mass % of styrene monomer units and from 65 to 25 mass % of ~~(meth)arylate~~ (meth)acrylate monomer units, and from 1 to 15 parts by mass of a dispersed phase of an elastomer.

Please replace the paragraph beginning at page 5, line 8, with the following rewritten paragraph:

5. A multilayer sheet which comprises a substrate layer of an elastomeric styrene polymer comprising from 1 to 20 parts by mass of a dispersed phase of an elastomer comprising from 30 to 50 mass % of styrene monomer units and from 70 to 50 mass % of butadiene monomer units, and from 99 to 80 parts by mass of a continuous phase of a polymer comprising from 35 to 75 mass % of styrene monomer units and from 65 to 25 mass % of (meth)acrylate monomer units, and a surface layer of a styrene polymer comprising from 35 to 75 mass % of styrene monomer units and from 65 to 25 mass % of ~~(meth)arylate~~ (meth)acrylate monomer units, formed on each side of the substrate layer.

Please replace the paragraph beginning at page 5, line 20, with the following rewritten paragraph:

6. The sheet according to Item 5, wherein the styrene polymer comprises at most 3 parts by mass of a dispersed phase of an elastomer comprising from 30 to 50 mass % of styrene monomer units and from 70 to 50 mass % of butadiene monomer units, and from 97

Application No.: 10/505,447

Reply to Advisory Action of: October 16, 2007

to less than 100 parts by mass of a continuous phase of a polymer comprising styrene monomer units and ~~(meth)arylate~~ (meth)acrylate monomer units.